



74 Kent Street
Brooklyn, New York 11222-1517

Phone (718) 383-5080
Fax (718) 383-7445
E-mail: dllabs@aol.com

Accredited by National Voluntary Laboratory Accreditation Program - Lab Code 100252
Accepted by Canadian General Standards Board - No. 76005 - ISO/IEC 25 Approved

December 23, 2002

Textured Coatings of America
2422 East 15th Street
Panama City, FL 32405

Attn: **Ms. Eileen Dutton**
Senior Chemist

DL - 13683D-R

OBJECTIVE

To determine the flame spread and smoke generated on a submitted coating system.

PRODUCTS TESTED

Tex - Cote SuperCote Textured primer under SuperCote TopCote

TEST PROCEDURE

The primer was applied on 1/4" cement board at a spreading rate of 55 sq. ft./gal. The topcoat was applied at a spreading rate of 150 sq. ft./gal. The coating was allowed to dry for thirty days and then tested for flame spread and smoke development following procedures outlined in ASTM E 84.

TEST RESULTS

The test results are shown below:

<u>Substrate</u>	<u>Flame Spread Index</u>	<u>Smoke Developed Index</u>
Cement	0	0
Red Oak Flooring	100	100
Test Board	10	0

Note: Cement and Red Oak Flooring were used to standardize the test equipment.

This report may contain test data obtained from test methods not covered by NVLAP accreditation. See reverse side for those test methods which are covered.
This report shall not be reproduced except in full without the prior written approval of the DL Labs, Inc. The information contained herein is not endorsed by NVLAP, CGSB or any agency of the U.S. or Canadian governments and no such endorsement may be claimed.



Textured Coatings of America
Re: DL - 13683E - R

CONCLUSION

Based upon the test results, the submitted sample of Tex-Cote SuperCote Classic Primer under SuperCote Topcoat system meets the Class A flame spread requirement of a flame spread less than 25 as per ASTM E 84, exhibiting a flame spread of 10.

DL Labs, Inc.

A handwritten signature in black ink, appearing to read 'Thomas J. Sliva'.

Thomas J. Sliva
Vice President/
Technical Director

mb

cc: M. Lazaro, Jr.